



### HIGH PERFORMANCE THERMAL INTERFACE PRODUCTS

Tgard<sup>TM</sup> 100 is a high thermal performance insulator pad consisting of silicone/boron nitride composite. It is specially designed to maximize high thermal and electrical isolation performance for wide variety of applications.

The unique formulation offers an excellent smooth and compliant surface which minimizes interfacial thermal resistance at low mounting forces. Tgard<sup>TM</sup> 100 is ideal for applications that require low component mounting forces include discrete semiconductors mounted with clips.

### FEATURES AND BENEFITS

- High thermal conductivity of 3.5W/mK
- High breakdown voltage of 6,000 volts
- Thermal resistance of 0.279°C-in<sup>2</sup>/W @ 50psi
- Unique formulation minimizes thermal resistance at low mounting forces

### MARKETS

- Switch mode power supplies for:
  - Communications
  - Consumer Electronics
  - Industrial
  - Instrumentation
  - Medical
- Motor controllers
- Power conversion equipment
- Power Semiconductors

USA: +1.423.308.1690  
Europe: +42.0.4885.7511.1  
Asia: +86.022 66298160

THR-DS-Tgard 100 1215

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2015 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights. Version A01

PROPERTIES	TEST METHOD	METRIC VALUES		IMPERIAL VALUES	
<b>ELECTRICAL PROPERTIES</b>					
Dielectric breakdown voltage 50mm probe	ASTM D149	Avg > 6,000 volts AC		Avg > 6,000 volts AC	
Volume resistivity	ASTM D257	10 <sup>12</sup> ohm-cm		10 <sup>12</sup> ohm-in	
Dielectric constant @ 1MHz	ASTM D257	5.0		5.0	
<b>MECHANICAL PROPERTIES</b>					
Thickness		0.254 mm		10 mils	
Hardness	ASTM D2240	90 Shore A		90 Shore A	
Operating temperature range	N/A	-60°C to 180°C		-76°F to 356°F	
Color	N/A	White		White	
UL flammability rating	UL 94	V-0		V-0	
<b>PRESSURE</b>					
	<b>UNITS</b>	<b>10</b>	<b>25</b>	<b>50</b>	<b>100</b>
		<b>(69)</b>	<b>(172)</b>	<b>(345)</b>	<b>(689)</b>
Modified ASTM D5470	°C <sup>-2</sup> /watt	0.378	0.327	0.279	0.249
Modified ASTM D5470	°C <sup>-2</sup> /watt	2.439	2.109	1.801	1.606
T0-220	°C/watt	0.782	0.754	0.718	0.673

Standard thickness: 10 mils (0.254mm)

Configurations available: Sheet form, roll form and die-cut parts

Single side, pressure sensitive adhesive on request

Standard options: Without adhesive (A0): 9" x 18" sheet , With adhesive (A1): 9" x 18" sheet

Custom die-cut parts: Custom configurations available with standard tolerance of 0.5mm (0.020")

USA: +1.423.308.1690  
 Europe: +42.0.4885.7511.1  
 Asia: +86.022 66298160

THR-DS-Tgard 100 5-28-2018

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2015 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights. Version A01

[www.lairdtech.com](http://www.lairdtech.com)